

## **BITUCOAT-PLUS**

### ***RUBBERISED WATERPROOFING COATING***



#### **DESCRIPTION:**

Bitucoat-Plus is a rubberized waterproof coating, based on synthetic rubber and organic chemicals. It is a single component, ready to use black coating which can be applied to dry or damp surfaces.

#### **ADVANTAGE**

- ✓ It provides excellent elasticity
- ✓ Single component, ready to use coating
- ✓ Resistant to temperatures around 80-90 deg. C.
- ✓ Cost effective and long lasting

#### **AREAS OF APPLICATION:**

Bitucoat-Plus can be used for waterproofing of terraces, parapet walls, AC/GI Sheets, gutters, roofs of buses, car chassis etc. and is extremely useful for coating for inside and outside water tanks.

**SPECIFICATION:**

|                    |   |
|--------------------|---|
| Base               | Bitumen   |
| Colour             | Black   |
| Appearance         | Semi-Viscous Liquid                               |
| System             | Single Component                                  |
| Finish             | Smooth & Semi-Glossy                              |
| Drying Time:       |   |
| Surface Dry        | 3-4 Hours   |
| Hard Dry           | 6-8 Hours   |
| Recommended Coats  | 1-2   |
| Coverage           | 40-55 sq.ft./Litre/Coat on smooth masonry surface |
| Resistance to Heat | 80-90° C.   |
| Flash Point        | Above 40° C.                                      |

**PREPARATION:**

Remove all existing treatments if any. Clean the surface of dust, loose particles, oils and grease. Apply one coat of Bitu Sealer as primer coat. Let it dry for 4-6hours. Now all cracks including all hairline cracks will be visible. Fill the cracks of 1 to 5 mm width with **BITUFILL** with putty knife, spatula/finger. Avoid formation of cavities or bubbles. Allow to dry for 24 hours. Inspect the cracks if filled properly. If shrinkage is observed, then top up once again with **BITUFILL** to the level of surface.

**METHOD OF APPLICATION:**

Stir the contents thoroughly prior to use. Apply first coat of **BITUCOAT-PLUS** on prepared surface. Allow to dry for 8 hours or overnight. Apply second coat of **BITUCOAT-PLUS**. If subsequent coats are required, they must be applied at intervals of 8 hours between each coat.

**CLEANING OF TOOLS :**

Wash hands and tools with MTO.

**SAFETY PRECAUTIONS:**

Protective gear such as gloves and goggles should be worn when handling the product. Treat any splashes to the skin or eyes with fresh water immediately. Should the product be accidentally swallowed, do not encourage vomiting, but call for immediate medical assistance. Ensure that the container is available for medical attendant to examine any relevant instructions and content details.

**PACKING:**

Available in 4 & 20 Litres.

***WARRANTY CLAUSE:*** The product incorporated and sold is without Warranty expressed or implied, including warranty of Merchantability and fitness for use of this material and upon condition that purchaser shall make the own test to determine the suitability and quality of such products for their particular purpose. The user assumes all risks of use and handling, whether or not in accordance with any statement of the supplier. Supplier's liability if any, for any action arising out of the material being supplied shall be limited to only replacement of material.