

ACE-BLOCK-GRP

BRICKS & BLOCKS FIXER



DESCRIPTION:

ACECOATS ACEBLOCK-GRP is a ready to use, polymer modified, eco friendly, wet mix, self curing bricks & blocks adhesive of any kind. The product is designed to save water, labour and time to make conventional mortar fixer.

ADVANTAGES:

- Single component, ready to use.
- Saves works labour & time.
- Eco friendly.
- No post curing with water needed.
- No cracking.

AREA OF APPLICATION:

ACECOATS ACEBLOCK-GRP is a bricks & blocks laying adhesive of any kind of masonry work.

SPECIFICATION:

Appearance	Grey viscous paste
Consistency	Thick flowable viscous paste
Density	1.43 – 1.47
Bond strength	Excellent
Shrinkage	Nil after drying
Coverage/25 kgs bag	ACC Block 625 X 240 X 200 = 100 – 110 Sq.Ft. ACC Block 625 X 240 X 150 = 120 – 130 Sq.Ft. ACC Block 625 X 240 X 125 = 130 – 140 Sq.Ft. ACC Block 625 X 240 X 100 = 140 – 150 Sq.Ft. FLY ASH BRICK 225 X 150 X 75 = 30 – 40 Sq.Ft. FLY ASH BRICK 225 X 100 X 75 = 45 – 50 Sq.Ft. CONCRETE BLOCK 390X290X150 = 60 – 70 Sq.Ft.
Pulloff Adhesion @ 7 Days	1.35 (N/mm ²) (ASTM D4541 method)

PREPARATION & APPLICATION:

Take out the material in a pot & mix well with trowel or spatula.

Apply the material in 1.5 – 2 mm on the block with help of notched trowel.

CLEANING OF TOOLS:

Wash all containers, brushes, tools and hands with water.

SAFETY PRECAUTIONS:

Protective gear such as gloves and goggles should be worn when handling the product. Treat any splashes to the skin or eyes with fresh water immediately. Should the product be accidentally swallowed, do not encourage vomiting, but call for immediate medical assistance. Ensure that the container is available for medical attendant to examine any relevant instructions and content details.

PACKING:

Available in 25 kgs.

WARRANTY CLAUSE: *The product incorporated and sold is without Warranty expressed or implied, including warranty of Merchantability and fitness for use of this material and upon condition that purchaser shall make the own test to determine the suitability and quality of such products for their particular purpose. The user assumes all risks of use and handling, whether or not in accordance with any statement of the supplier. Supplier's liability if any, for any action arising out of the material being supplied shall be limited to only replacement of material.*



Test Order/Report No.:BVIPL: SPL : 25941C/150/1/2016
Date of Receipt : 11.01.2016

Date : 21.01.2016
Page 1 of 1

ASSOCIATED CHEMICALS

Plot No.C-17, Tran Thane Ind Area, MIDC, Thane Belapur Road,
Post Khairne, Dist Thane – 400601.

TEST REPORT

Source of sample : Sample supplied by the customer.
Number of samples tested : 01(One Only).
Customer's Reference : Letter dt.11.01.2016
Sample Description* : ACEBLOCK-GRP(Block/Brick Adhesive Mortar)
Lab Reference Number : 2016/JAN/09930
Condition of sample : Satisfactory
Period of Test : 14.01.2016 to 21.01.2016
Test Method : ASTM D4541

PHYSICAL PROPERTIES :

Sl. No.	Test Conducted	Results	Test Method
1	Pulloff Adhesion @ 7 Days (N/mm ²)	1.35	ASTM D 4541

* As furnished by the customer.

- Note:
1. The results relate only to the items tested.
 2. Report shall not be reproduced except in full, without the written approval of the lab.
 3. Any correction invalidates this report.

For **BUREAU VERITAS (INDIA) PVT LTD.**

Construction Services Laboratory



Dinesh Burde


Authorised Signatory

SPL/W135